

# Fukushima: Highly Radioactive Cesium-Bearing Microparticles Released into Japan's Natural Environment. Impacts on Human Health

By [Noriko Yamaguchi](#), [Masanori Mitome](#), [Maki Asano](#), [Kouji Adachi](#), and [Toshihiro Kogure](#)

Global Research, March 01, 2016  
[Nature](#) 3 February 2016

Region: [Asia](#)

Theme: [Environment](#), [Science and Medicine](#)

In-depth Report: [Nuclear War](#)

## Abstract

*Microparticles containing substantial amounts of radiocesium collected from the ground in Fukushima were investigated mainly by transmission electron microscopy (TEM) and X-ray microanalysis with scanning TEM (STEM). Particles of around 2 μm in diameter are basically silicate glass containing Fe and Zn as transition metals, Cs, Rb and K as alkali ions, and Sn as substantial elements. These elements are homogeneously distributed in the glass except Cs which has a concentration gradient, increasing from center to surface. Nano-sized crystallites such as copper- zinc- and molybdenum sulfide, and silver telluride were found inside the microparticles, which probably resulted from the segregation of the silicate and sulfide (telluride) during molten-stage. An alkali-depleted layer of ca. 0.2 μm thick exists at the outer side of the particle collected from cedar leaves 8 months after the nuclear accident, suggesting gradual leaching of radiocesium from the microparticles in the natural environment.*

## Introduction

Although almost five years have passed since the accident of Fukushima Daiichi Nuclear Power Plant (FDNPP), radioactive contamination in the surrounding area is still a serious problem in Japan. The largest radionuclide deposition event occurred on March 15–16 and the second largest on 21–23, 2011. Wet deposition was a major source of radiocesium contamination of terrestrial environment<sup>1</sup>, while contribution of dry deposition was larger near the FDNPP<sup>2</sup>. In order to understand and predict the fate of radioactive materials contaminating the terrestrial environment, it is important to clarify the physicochemical properties of the deposited materials. From previous cases of radionuclide release, it is known that the chemical species of released radiocesium is monovalent cation (Cs<sup>+</sup>) which is soluble<sup>3</sup>. Deposition of radiocesium as insoluble particles has also been pointed out. Autoradiography analyses using imaging plate (IP) showed spots of particulate materials on plant tissues collected from Fukushima<sup>4,5,6</sup>. On the aerosol filter collected from March 14–15, 2011 in Tsukuba, 170 km south-southwest of FDNPP, Adachi *et al.*<sup>7</sup> discovered spherical particulate radiocesium of 2.0–2.6 μm in diameter, with particles insoluble in water having a glass-like structure<sup>8</sup>. These microparticles contain several fission products of U-235 other

than radiocesium, and Fe and Zn which are also used in nuclear reactors<sup>8</sup>. Hence, they were considered to be released directly from nuclear reactors.

Kaneyasu *et al.*<sup>9</sup> suggested that vaporized radiocesium was transported with sulfate aerosol in the air, dissolved to cloud droplets and fell as rain. On the aerosol filter collected on March 20–21, 2011, rainy days in Tsukuba, the majority of radiocesium was in water-soluble form<sup>7</sup>. Such water-soluble radiocesium that reached the ground surface as a solute was fixed to soils, especially to clay minerals<sup>10</sup>. In the terrestrial environment, the majority of radiocesium is present in solid form regardless of the initial form of deposition. However, compared to clay minerals originally contaminated by soluble radiocesium in soil, the solid radiocesium, which was initially deposited as radioactive microparticles, had stronger radioactivity. Although the contribution or percentage of such radioactive microparticles in the contamination level of Fukushima has not been evaluated, its influence on human health may be serious in terms of its intense radioactivity. Moreover, the structural detail of the microparticles may give insights into the state of the broken reactor and fuel debris.

In the present study, we investigated radioactive microparticles, similar to those reported by Adachi *et al.*<sup>7</sup>, but collected from the ground, by observing their internal structure with transmission electron microscopic (TEM) techniques.

(...)

[Read full article here](#)

The original source of this article is [Nature](#)

Copyright © [Noriko Yamaguchi](#), [Masanori Mitome](#), [Maki Asano](#), [Kouji Adachi](#), and [Toshihiro Kogure](#), [Nature](#), 2016

---

[Comment on Global Research Articles on our Facebook page](#)

[Become a Member of Global Research](#)

Articles by: [Noriko Yamaguchi](#), [Masanori Mitome](#), [Maki Asano](#), [Kouji Adachi](#), and [Toshihiro Kogure](#)

**Disclaimer:** The contents of this article are of sole responsibility of the author(s). The Centre for Research on Globalization will not be responsible for any inaccurate or incorrect statement in this article. The Centre of Research on Globalization grants permission to cross-post Global Research articles on community internet sites as long the source and copyright are acknowledged together with a hyperlink to the original Global Research article. For publication of Global Research articles in print or other forms including commercial internet sites, contact: [publications@globalresearch.ca](mailto:publications@globalresearch.ca)

[www.globalresearch.ca](http://www.globalresearch.ca) contains copyrighted material the use of which has not always been specifically authorized by the copyright owner. We are making such material available to our readers under the provisions of "fair use" in an effort to advance

a better understanding of political, economic and social issues. The material on this site is distributed without profit to those who have expressed a prior interest in receiving it for research and educational purposes. If you wish to use copyrighted material for purposes other than "fair use" you must request permission from the copyright owner.

For media inquiries: [publications@globalresearch.ca](mailto:publications@globalresearch.ca)